

CLAIMS

What is claimed is:

- 5 SUB A3
1. A process for fabrication of a semiconductor device including an ONO structure, comprising forming the ONO structure by:
providing a semiconductor substrate having a silicon surface;
forming a first oxide layer on the silicon surface;
depositing a silicon nitride layer on the first oxide layer; and
forming a top oxide layer on the silicon nitride layer,
wherein the top oxide layer is formed by an in-situ steam generation oxidation of a surface of the silicon nitride layer.
 - 10 2. The process of claim 1, wherein the semiconductor device comprises a two-bit EEPROM device or a floating gate FLASH device.
 - 15 3. The process of claim 2, wherein the semiconductor device is a two-bit EEPROM device in which the first oxide layer is a tunnel oxide layer, and the tunnel oxide layer is formed by an in-situ steam generation oxidation of the silicon surface.
 - 20 4. The process of claim 2, wherein the semiconductor device is a floating gate EEPROM device in which the first oxide layer is a bottom oxide layer, and the bottom oxide layer is formed by an in-situ steam generation oxidation of the silicon surface.
 - 25 5. The process of claim 1, wherein the steps of forming an oxide layer, depositing a silicon nitride layer and forming a top oxide layer are carried out in an RTP and RTCVD apparatus.
 - 30 6. The process of claim 1, wherein the steps of forming an oxide layer, depositing a silicon nitride layer and forming a top oxide layer are carried out in a single-wafer cluster tool.

7. The process of claim 1, wherein the silicon nitride is deposited by RTCVD.

8. The process of claim 1, wherein each step of in-situ steam generation oxidation is carried out by providing a hydrogen-containing gas and an oxygen-containing gas to an RTP system or to a single-wafer cluster tool.

SUB
A5

9. The process of claim 1, wherein the in-situ steam generation oxidation is carried out at a temperature in the range from about 850°C to about 1150°C.

10. The process of claim 1, wherein the step of depositing a silicon nitride layer comprises RTCVD using about 0.5 to 2 slpm ammonia and about 20 to about 50 sccm of a second gas selected from the group consisting of silane and dichlorosilane.

11. The process of claim 10, wherein the RTCVD process comprises a three step sequence including a temperature ramp up step, a deposition step of about 2 minutes, and a cool down step.

12. The process of claim 1, wherein the silicon nitride layer is deposited to a thickness of about 50 to about 300 angstroms.

13. The process of claim 1, wherein the top oxide layer is formed to a thickness of about 50 to about 150 angstroms.

14. A process for fabrication of a semiconductor device, the device including a two-bit EEPROM device including an ONO structure, comprising forming the ONO structure by:

- providing a semiconductor substrate having a silicon surface;
- forming a tunnel oxide layer overlying the silicon surface;
- depositing a silicon nitride layer overlying the tunnel oxide layer; and

A67 forming a top oxide layer overlying the silicon nitride layer by in-situ steam generation oxidation of a portion of the silicon nitride layer.

5 15. The process of claim 14, wherein the steps of forming a tunnel oxide layer, depositing a silicon nitride layer and forming a top oxide layer are carried out in an RTP apparatus which is a component of a single-wafer cluster tool.

16. The process of claim 14, wherein the silicon nitride is deposited by RTCVD.

10 17. The process of claim 12, wherein each step of in-situ steam generation oxidation is carried out at a temperature in the range from about 850°C to about 1150°C and by providing hydrogen gas and oxygen gas to the RTP apparatus.

15 18. A process for fabrication of a semiconductor device, the device including a floating gate FLASH structure comprising an ONO structure, comprising forming the ONO structure by:

providing a semiconductor substrate having a floating gate electrode;

forming a bottom oxide layer overlying the floating gate electrode;

depositing a silicon nitride layer overlying the tunnel oxide layer; and

20 forming a top oxide layer overlying the silicon nitride layer by in-situ steam generation oxidation of a portion of the silicon nitride layer.

25 19. The process of claim 18, wherein the steps of forming a bottom oxide layer, depositing a silicon nitride layer and forming a top oxide layer are carried out in an RTP apparatus which is a component of a single-wafer cluster tool.

20 20. The process of claim 18, wherein the silicon nitride is deposited by RTCVD.

AF01120

A77

21. The process of claim 18, wherein each step of in-situ steam generation oxidation is carried out at a temperature in the range from about 850°C to about 1150°C and by providing hydrogen gas and oxygen gas to the RTP apparatus.

10023548:121701